



[www.andelaproducts.com](http://www.andelaproducts.com)

| <b><u>Post-Consumer Recycled Andela Glass Products</u></b> |                            |
|------------------------------------------------------------|----------------------------|
| <b><u>Technical Data</u></b>                               |                            |
| Available Sizes (US Mesh)                                  | 4 mesh minus, 2 mesh minus |
| Volume/Ton - Avg                                           | 26.5 Ft <sup>3</sup>       |
| Loss On Ignition                                           | 0.03%                      |
| Biochemical Oxygen Demand                                  | 0 PPM                      |
| Softening Point                                            | Approx. 1350°F             |
| Specific Gravity                                           | 2.5                        |
| Bulk Density - Avg                                         | 84 Lb./Ft <sup>3</sup>     |
| Shape                                                      | Sub-angular, Non-porous    |
| Hardness                                                   | 5.5-6.0 Mohs               |
| Micro Hardness                                             | 542 HK                     |
| Reactivity                                                 | Inert, No heavy metals     |